


Flat Glazing

**FLEXIBLE
LIGHT IN WEIGHT
RANGE OF SIZES**



**Acrylic Sheet Exterior
Polystyrene Sheet Interior Grade
Solid Polycarbonate Sheet**



Corotherm Flat[®]

Solid Polycarbonate Sheet

INTERIOR &
EXTERIOR USE

FEATURES

Very high impact resistant
Much safer than glass
Flexible
High light transmission
UV resistant
Suitable for interior & exterior use

APPLICATIONS

Primary Glazing
Secondary Glazing
Areas Where Security is Vital
Whenever Vandalism is Possible
Screen Guards & Visors

1

Cutting

Carefully score the sheet until nearly halfway through and right up to the edges, using a cutting knife with a scoring blade, against a firm straight edge, clamping the sheet to avoid slipping. It is best to score the sheet on a firm flat surface.

Place the sheet on a firm table, with the scored cutting line upwards and along the edge of the table, then apply even pressure downwards to break the sheet along the scored line. When breaking the sheet support all the sheet fully along the scoreline. If any irregularities occur, they can be smoothed with an emery board or filing plane.

N.B. It will not be possible to cut Corotherm Flat using this method. See sawing guidelines below.

2

Sawing

Ariel Glazing Sheets can be sawn, either singly or several sheets together. Use an electric jigsaw or a handsaw with a fine toothed blade at a shallow angle. Sawing is better than cutting and dividing if just a thin strip needs to be removed from a sheet. For cutting curves, use an electric jigsaw which has a scrolling feature. When using a jigsaw set the pendulum stroke to zero and when cutting curves always ensure the sheet is fully supported.

3

Drilling

Slow speed power drills or hand drills are both suitable for drilling Glazing Sheets and should be used with a metal working bit. Prevent the drill point from skipping by marking the hole position with a bradawl or by applying a small piece of adhesive tape where the hole is to be made. Use light pressure and back the sheet with a piece of wood to help prevent the sheet from chipping where the drill bit emerges. Make holes 3mm larger than fixings to allow for thermal movement.

4

Fixing

Ariel Glazing Sheet can be fixed using suitable proprietary fasteners, jointing strips, adhesives and sealants. Leave 3mm clearance around the edges of the panels to allow for thermal movement. Do not remove the protective film until the piece is ready to be fitted. Corotherm Flat can be installed in most types of frames including PVC, wood and aluminium. The framing system must retain the sheet but allow for thermal movement. Only compatible sealants must be used, these include silicone, EPDM, neoprene or 'plasticiser free' chloroprene materials of proven performance. Please note that PVC gaskets are not suitable for use with polycarbonate.

Liteglaze Glazing Strip



The Liteglaze Glazing Strip can fix Ariel's glazing materials from 2mm to 4mm as secondary glazing to an existing window frame. The double sided adhesive tape means it can be fixed to either wood or metal frames securely. For larger wooden windows it is recommended that the strip is screw fixed. The 'snap-in' cap makes installation both quick and easy. It is also suitable for fitting Styrene in internal situations e.g. internal door panels, wallpaper protection etc.

Thermal Expansion Allowance

Product Type	Co-efficient of Thermal Expansion mm/m°C	Expansion Allowance per metre of sheet (mm)	Hole Size
Corotherm Flat	0.067	4.5	Shank Diameter +6mm for first metre of sheet and 4.5mm for each subsequent metre

Cleaning

Use anti-static cleaner or warm soapy water to clean, also suitable for use with Styrene and Corotherm Flat.

DO NOT USE glass cleaner, abrasives or squeegees.

Glazing Sheet Dimensions

DIMENSIONS (MM)	600 x 1200	600 x 1800	900 x 1200	1200 x 1200	1200 x 1800	1200 x 1830	1200 x 2400	1220 x 2400
-----------------	---------------	---------------	---------------	----------------	----------------	----------------	----------------	----------------

Corotherm Flat
(4mm and 6mm)

•

•



Contact our sales team:

Tel: 01246 281111

Orderline Email: sales@arielplastics.com
or visit www.arielplastics.com

Corotherm Flat®

Solid Polycarbonate Sheet



Ariel Plastics Ltd

Speedwell Industrial Estate
Staveley
Derbyshire
S43 3JP

Tel: 01246 281111

Fax: 01246 561111

Email: info@arielplastics.com

Web: www.arielplastics.com